

MANHATTAN

Type of leather:	bovine
Origin:	European and non-European
Thickness:	1,3 - 1,5 mm
Size:	3,8 - 4,2 sqm
Tannage:	chrome salts
Dye:	aniline dye
Finishing:	pigmented
Appearance:	semi-gloss

SPECIFICATIONS*

ANALYSIS	TEST METHOD	UNIT OF MEASUREMENT	RECOMMENDED VALUE
Colour fastness to dry rubbing 500 cycles	UNI EN ISO 11640 UNI EN ISO 11641	Grey scale	4
Colour fastness to wet rubbing 250 cycles	UNI EN ISO 11640 UNI EN ISO 11641	Grey scale	3/4
Colour fastness to alkaline sweat 80 cycles	UNI EN ISO 11640 UNI EN ISO 11641	Grey scale	3/4
Finish adhesion	UNI EN ISO 11644	N/cm	2
pH	UNI EN ISO 4045	-	3,2
Tear strenght	UNI EN ISO 3377-1	N	20
Colour fastness to light xenotest	UNI EN ISO 105 B02	Blue scale	4
White Colour	UNI EN ISO 105 B02	Blue scale	3
Flammability	UNI EN 1021-1:2006	-	No ignition
Flammability	UNI EN 1021-2:2006	-	No ignition

*All submitted tests results are obtained using official methods on non-manipulated leather. Further tests made after using leather, must be agreed between the producer and the buyer.

new pel company S.r.l. | Viale Vicenza, 56 | C.P. 43 | 36071 ARZIGNANO (VI) Italy | Tel. +39 0444 542258
r.a. | Fax +39 0444 674255

E-mail: info@newpel.com | www.newpel.com | C.F. e P. IVA IT 00884830241 | R.E.A. 190592/VI | Cap.
Soc. € 1.300.000 int. Vers.